



	COLOUR	APPLICATION									APPEARANCE		MIXING		DRYING			PAGE
		STEEL	E-COATING	GALVANIZED	ALUMINIUM	ALUMINIUM RIMS	FIBERGLASS	HARD PLASTIC	SOFT PLASTIC	SPECIFIC WEIGHT kg/l	PACKAGING kg/liter	MIXING RATIO % by weight	POTLIFE at 20°C.	SANDING TIME at 20°C.	SANDING TIME IR 60°C.	TEMP. RESISTANCE °C		
<b>GAP 00</b>	<b>GAPOL</b>	●●	●●	●●	●●	●●	●●	●●	●●	1,83	2kg/1,09l	2%	4-5'	<25'	10'	80 °C	<b>64</b>	
<b>GAP 10</b>	<b>MULTI</b>	●●		●	●		●●		1,81	2kg/1,10l	2%	4-5'	<20'	5'	80 °C	<b>64</b>		
<b>GAP 20</b>	<b>FINE</b>	●●					●		1,68	2kg/1,19l	2%	4-5'	<15'	10'	80 °C	<b>64</b>		
<b>GAP 25</b>	<b>SELF-LEVELLING</b>	●●					●		1,16	1kg/0,85l	2%	3'	15-20'	5-10'	80 °C	<b>65</b>		
<b>GAP 30</b>	<b>LIGSHT</b>	●●		●	●		●●		1,36	1,5kg/1,09l	2%	4-5'	<15-20'	5-10'	80 °C	<b>66</b>		
<b>GAP 31</b>	<b>ULTRA LIGHT</b>	●●	●	●	●		●●		1	1kg/1l	1-3%	3-5'	<30'	4'-5'	80 °C	<b>66</b>		
<b>GAP 33</b>	<b>EXTRA LIGHT</b>	●●	●	●	●		●●		1	3kg/3l	1-3%	3-5'	<30'	4'-5'	80 °C	<b>66</b>		
<b>GAP 40</b>	<b>FIBER</b>	●			●		●●		1,61	1,8kg/1,11l	2%	4-5'	<20'	10'	80 °C	<b>67</b>		
<b>GAP 50</b>	<b>ALU</b>	●●		●●	●●	●●	●		1,53	2kg/1,30l	2%	4-6'	<20'	10'	80 °C	<b>67</b>		
<b>GAP 70</b>	<b>PLASTFILL</b>						●	●●	1,3	1kg/0,75l	1-3%	3-5'	<30'	4'-5'	80 °C	<b>68</b>		
<b>GAP 90</b>	<b>LIGHT AND EASY</b>	●●		●●			●	TSP 030	1,24	1,9kg/1,5l	2%	3-4'	15-20'	5-10'	80 °C	<b>69</b>		
<b>GAP 93</b>	<b>LIGHT AND EASY</b>	●●		●●			●	TSP 030	1,24	3,9kg/3l	2%	3-4'	15-20'	5-10'	80 °C	<b>69</b>		
<b>DEB 12</b>	<b>PB - SN</b>	●●		●●	●●	●●		TSP 030	1,3	1L/1,3kg	1-3%	3-4'	<30'	-	180° C MAX 15'!	<b>67</b>		

**Hardener**

- GAP 52** for all GAP putties
- DEB 51** for DEB 12

**Storage**

Shelf life putty: 18 months  
Shelf life BPO hardener: 12 months

- Very suitable
- Suitable



Dry



Frost free



Not in direct sunlight



Closed tin